



Technical Information

Product name	: MoTip Clear Lacquer		
Contents	: 500 ml High Gloss	500 ml Matt	150 ml High Gloss
Article number	: 04009	04000	02001
Supplier / Producer	: MOTIP DUPLI B.V.		
	Wolfraamweg 2		
	NL-8471 XC WOLVEGA		
	Telephone number	+31 561 – 69 44 00	
	Telefax number	+31 561 – 69 44 31	

Product description

High quality clear lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone, and various types of plastic.

Product characteristics

Fast drying
Excellent filling property
Lasting gloss
Scratch free and shock proof
Resistant to weather influences
Corrosion preventive
UV-resistant and non-fading
Excellent adhesion

Physical and Chemical Characteristics

Contents	: 500 ml	150 ml
Base	: Acrylic resin	
Colour	: Transparent	
VOC-content	: Approximately 90% w/w	
Solid content	: Approximately 10% w/w	
Gloss	: High gloss	90 at an angle of 60°
	Matt	15 at an angle of 60°
Coverage	: 1,5 to 2 m ²	Approximately 0,5 m ²
Dust dry	: After 5 to 10 minutes	
Tack free	: After 10 to 20 minutes	
Hardened/re-sprayable	: After 2 hours	
Heat resistant	: To 110°C	

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the clear lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.